

POSTER PRESENTATION

Open Access

# Thrombus-specific manganese-based “nanobialys” for MR molecular imaging of ruptured plaque

Dipanjan Pan<sup>1\*</sup>, Shelton D Caruthers<sup>1</sup>, Angana SenPan<sup>1</sup>, Anne H Schmieder<sup>1</sup>, Todd A Williams<sup>1</sup>, Michael J Scott<sup>1</sup>, Patrick J Gaffney<sup>2</sup>, Samuel A Wickline<sup>1</sup>, Gregory Lanza<sup>1</sup>

From 15th Annual SCMR Scientific Sessions  
Orlando, FL, USA. 2-5 February 2012

## Summary

Mathematical modeling studies have suggested that non-spherical, disc-shaped nanoparticles may have optimal intravascular flow and homing characteristics. In this study, we report the development of a fibrin-specific high-relaxivity bialy-shaped polymeric nanoparticle using porphyrin-chelated manganese. We anticipate that this agent would be highly effective for molecular imaging of microthrombi in ruptured atherosclerotic plaques.

## Background

Detection of microthrombi within fissures of vulnerable atherosclerotic plaques requires a sensitive molecular imaging contrast agent. Moreover, recent reports based on mathematical modeling suggest that nonspherical, disc-shaped nanoparticles could have improved intravascular flow characteristics, which may improve ligand-directed targeting. In light of the concern surrounding the use of gadolinium in patients with severe renal disease, the goal of this research was to develop a nonspherical fibrin-targeted manganese-based molecular imaging agent.

## Methods

A new class of manganese (III)-labeled, a toroidal-shaped, vascularly-constrained nanoparticles, “nanobialys (MnNBs)”, was designed, synthesized, physically characterized, and evaluated for MR properties. Single slice inversion recovery and multi-echo spin echo sequences were used to calculate the ionic (per metal) and particulate (per particle) relaxivities from 7 serial dilutions of nanobialys at 1.5T and 25°C. Fibrin clots

supported on silk suture suspended in PBS were targeted with MnNB or control (non-paramagnetic) NB to the fibrin clots with avidin-biotin interactions and fibrin-specific antibodies (NIB5F3). Magnetic resonance images (3T) of the clots were acquired using T1-weighted gradient echo techniques.

## Results

Mn-nano-bialys were 190nm ± 5nm with polydispersity of 0.26±0.01. (Fig 1) In the hydrated state, Manganese content was 25.6 ± 03 µg/mL by ICP OES, i.e., 165,000 Mn(III) per nanobialy. The particulate relaxivities of the MnNB were high,  $r_1=612,307\pm 7213$  and  $r_2= 866,989 \pm 10704$  (s•mmol [nanobialy])<sup>-1</sup> measured at 1.5T (25°C), with ionic  $r_1$  and  $r_2$  relaxivities of 3.7±1.1 and 5.2 ±1.1 (s•mmol [Mn])<sup>-1</sup>, respectively. MR imaging of MnNB targeted to fibrin clot phantoms showed clear contrast enhancement, while control clots had no (p<0.05) contrast change (Fig 2).

## Conclusions

Fibrin-specific MnNBs are a novel, high relaxivity, non-gadolinium, molecular imaging agent that offers a sensitive noninvasive MR imaging approach for diagnosis of ruptured atherosclerotic plaques.

## Funding



NIH.

## Author details

<sup>1</sup>Medicine, Washington University, Saint Louis, MO, USA. <sup>2</sup>Surgery, Saint Thomas', London, UK

Published: 1 February 2012

<sup>1</sup>Medicine, Washington University, Saint Louis, MO, USA  
Full list of author information is available at the end of the article



doi:10.1186/1532-429X-14-S1-P136

Cite this article as: Pan *et al.*: Thrombus-specific manganese-based "nanobialys" for MR molecular imaging of ruptured plaque. *Journal of Cardiovascular Magnetic Resonance* 2012 **14**(Suppl 1):P136.

Submit your next manuscript to BioMed Central and take full advantage of:

- Convenient online submission
- Thorough peer review
- No space constraints or color figure charges
- Immediate publication on acceptance
- Inclusion in PubMed, CAS, Scopus and Google Scholar
- Research which is freely available for redistribution

Submit your manuscript at  
[www.biomedcentral.com/submit](http://www.biomedcentral.com/submit)

BioMed Central